

Spherinox-CR Premium Stainless Steel Cut Wire

FROHN

Average chemical analysis

C: max. 0,15%, Cr: 11,5-18,0%,
Ni: max. 0,75%, Si: max. 1,0%, Mn: max. 1,5%

Manufacturing standards / applicable specifications


Following consultation

Sizes

0,4 mm ~ CR 30	1,0 mm ~ CR 60
0,6 mm ~ CR 40	1,2 mm
0,8 mm ~ CR 50	1,6 mm

Other sizes on request

Grain shape



cylindrical



rounded

Hardness class new shot / Ready mixture

approx 300 HV ± 10%

Application fields

Blast cleaning, deburring, surface improvement, surface finishing

Applications

All kinds of aluminium castings, concrete stone industry

Packaging

1000 kg in 25 kg PE bags on EUR-pallets in cardboard box and shrinkwrap

Our sales engineers will assist you in the use of **Spherinox-CR Premium**. In addition, you can claim our free services.

There are no risks to health when **Spherinox-CR Premium** is used properly. **Spherinox-CR Premium** can be recycled.