

Stainless steel cut wire

FROHN

Design purpose

Surface hardening (shot peening), etc.

Material

1.4310 (AISI 302)

1.4016 (AISI 430)

1.4301 (AISI 304)

Other materials on request

Manufacturing standards / applicable specifications

e.g. AMS 2431/4, SAE J441

Sizes


0,3 mm	0,8 mm	1,4 mm
0,4 mm	0,9 mm	1,6 mm
0,5 mm	1,0 mm	1,8 mm
0,6 mm	1,1 mm	2,0 mm
0,7 mm	1,2 mm	2,2 mm

Other sizes on request

Grain shape



cylindrical



rounded

Hardness class

450 HV0.5/1 – 750 HV0.5/1 depending on size and grain shape

Packaging

- 25 kg PE bag on EUR-pallet (max 1000 kg)
- big bags max 500/1000 kg on expendable pallet
- 200 litre barrels max 800/1000 kg

Other packaging on request